



weaving a better world™

Industrial Fabrics

GEOMEMBRANES



TABLE OF CONTENTS

About Us 4

Manufacturing Capabilities 7

Quality Control 9

 Commitment to Quality. 9

 Product Development and Commercialization 9

 Quality Organization 9

 Quality Facilities 10

 Quality Assurance. 10

 Quality Control Capabilities 10

 Sampling and Inspection Plans. 11

 Inspection Records. 11

 Verification and Approval. 11

 Finished Product Packaging and Labelling 11

 Records Control and Documentation. 11

RhinoMat 13

RhinoSkin 30SG 14

RhinoSkin 12 - 30 mil 17

Fracking Containment Solutions 18

Installation Instructions 20

 Applications 20

 ASTM References. 20

 American Society for Testing and Materials (ASTM) 20

 Submittals 21

 Documents to be included in a submittal to the owner/
 engineer: 21

 InterWrap Qualifications 21

 Fabricators Qualifications 21

 Installer's Qualifications 21

 Geomembrane Arrival at Project Site. 21

 Unloading 21

 Storage 22

 Installation. 22

 Subgrade Preparation 22

Unfolding and Deploying Prefabricated Panels 22

Field Seaming. 22

Field Cleaning of Seams 23

Field Seaming. 23

Field Thermal Seaming (solid wedge only) 23

Field Tape Seaming 24

Field Seaming Test Requirements 24

Test Seams (Trial Seams) 24

Non-Destructive Testing (NDT) of Seam Testing. 25

Air Lance Testing (ASTM D 4437) 25

Mechanical Point Stress or "Pick" test (ASTM D4437) 25

Identification of Defects 26

Evaluation of Defects. 26

Geomembrane Penetrations. 26

 i. Pipes 26

 ii. Concrete 27

 iii. Drains 27

 iv. Aerators. 27

Cover Materials 27

Field Acceptance 28

Site Clean Up and Demobilization 28

InterWrap Family of Products 30

 Synthetic Roofing Underlayment 30

 Protective Packaging - Wood 30

 Protective Packaging - Metal 30

 Custom Coating & Laminating 30

ISO 9001:2008. 32

ISO 14001:2004. 33

ISO 18001:2007. 34

Key Contacts 35

 Sales - North America & Europe: 35

 Sales - India & Asia: 35

 Technical Support: 35


 Head Office: 35



weaving a better world™

ABOUT US

InterWrap® is a vertically integrated, global manufacturer of innovative coated woven products and diverse multi-layer laminated reinforced plastic substrates. InterWrap serves a wide variety of markets such as synthetic roofing underlayments, protective packaging - lumber & metal wrap, geomembranes, converted fabrics, agricultural and construction products. Consistent product quality is achieved by using state-of-the-art plastic extrusion, weaving, coating, laminating, printing techniques and a strong commitment to partnership with our customers, employees and suppliers.



COMPANY HIGHLIGHTS

- InterWrap® - since 1984
- ISO 9001:2008, 14001:2004 & 18001:2007 certified
- GAI - LAP Approved Laboratory
- Private corporation
- USD \$250 m+ for fiscal 2015
- Over 1200 employees worldwide
- Integrated manufacturer of coated woven polyolefin products
- Entrepreneurial, speed to market culture
- Growth of 20% per annum since inception
- Doubled in size over the past 3 years
- R&D focused
- Committed to environmentally sustainable solutions
- Lean manufacturing
- Expanding globally: Manufacturing, Distribution and Markets



MANUFACTURING CAPABILITIES

InterWrap's Headquarters are situated in Downtown Vancouver BC. Our two Canadian manufacturing facilities are located in Mission, British Columbia & Montreal, Québec. Our Canadian plants combined are equal to 300,000 square feet and are a key part of our North American manufacturing operations. Strategically positioned, these state-of-the-art facilities enable us to expedite goods to the West and East coasts of Canada and the U.S.A.

Established in 2002, InterWrap India has two strategically situated manufacturing plants in South East Asia that are fully equipped to manufacture coated woven fabrics, building and construction materials, industrial fabrics, lumber and metal wraps. Combined, our Dapada and Sayli plants occupy 250 000 square feet. They are a vital part of our manufacturing effectiveness and ability to successfully compete in global markets.

Established in 2007, our China facility is located in the Jiazhou province within very close proximity to two major export ports. With 290,000 square feet of world class manufacturing equipment and easy access to major shipping ports, our China manufacturing plant is ideally positioned to provide rapid delivery to our growing global clientele.

Our Charleston, SC location covers 170,000 square feet and is equipped for manufacturing and warehousing. Strategically situated on the East Coast of the United States this large facility allows InterWrap to serve our US East Coast clients even more efficiently.

- ISO 9001:2008, 14001:2004, 18001:2007 Certified
- GAI LAP - approved laboratory
- Over 1,000,000 sq ft of manufacturing space with a capacity of over 20, 000,000 LF per year
- Weaving looms; flat & circular, up to 144"
- Tape extrusion lines
- Extrusion coating lines, up to 144"
- Printing presses; up to 144" and 4 colors
- Slitting, cutting & rewinding machines
- Converting lines; sewing & heat sealing
- Laminating; paper, foil, film, non-woven





QUALITY CONTROL

Commitment to Quality

InterWrap Group is committed to provide a dependable supply of products and services that consistently meet the customer's expectations and all applicable product-specific standards. All business units of InterWrap Group operate on a quality business management system that is certified to an international standard ISO-9001:2008.

Product Development and Commercialization

The development and innovation of products is carried out through a robust product development and commercialization process. Verification and validation runs are performed to confirm that the process produces consistent results and the product meets design specifications before proceeding to full scale commercialized production.

Our research and development center is located in our Mission, B.C., Canada facility. This R&D center is used for developing and/or adjusting present product selection, as a display center and application testing with actual on going tests per market served.

Quality Organization

InterWrap's Quality team consists of a Quality Manager, R&D Manager and Process Engineers, Quality Assurance/Quality Control Coordinators, Quality testing facilities and manufacturing personnel. The team is responsible for ensuring the system is functioning correctly, that raw material and finished goods inspections are being conducted according to established protocols, and that established identification and traceability standards are maintained.

Quality Manager:

Maintenance and improvement of the MQA program. Development and approval of all raw material and finished fabric inspection plans.

R&D Manager, Process Engineers:

Product development and commercialization, including verification and validation trials. Approval of raw material specifications. Development and approval of all finished sheet product specifications.

QUALITY CONTROL

Quality Facilities

InterWrap’s manufacturing facilities maintain high capacity testing laboratories outfitted with modern equipment capable of performing most of the referenced tests.

InterWrap also utilizes hard and soft Quality Management database to house all of its raw material product specifications, raw material and finished fabric product inspection plans and records, and related process inspection data.

Quality Assurance

Incoming Raw Materials

InterWrap Group has developed and maintains full specifications for the resins used in the manufacture of Geomembranes sheet.

Resins

Resins are the base polyolefin materials used in the manufacture of Geomembranes fabrics. Each resin lot is provided with a product quality certification from the vendor. All incoming resins are inspected and tested prior to production use. Inspection results are entered into InterWrap’s different tools MS Log Quality Management Database.

InterWrap has developed clear policies for the identification and traceability of resin material to ensure that only tested and approved materials are used in the manufacture of Geomembrane fabric.

Additive Masterbatches

Various additive masterbatches are blended with natural resins in different proportions to achieve the desired properties of Geomembrane fabric. All masterbatches are purchased and verified against the approved material specifications before these are released to manufacturing.

Product Identification and Traceability

InterWrap has developed a system to identify the Geomembrane products. Each Geomembrane product is assigned with a unique product identifier or stock keeping unit (SKU). An enterprise resource planning (ERP) software is utilized to manage these product identifiers.

Each Geomembrane roll is labelled with the product identifier, job number, roll number and the product description. Details of the labelling specifications are provided in Appendix E - Finished Product Packaging and Labelling.

Any Geomembrane roll that does not meet the product specifications is identified and segregated to prevent its release or delivery. The process owner of a quality system database maintains the records of non-conforming Geomembrane products.

The traceability of raw materials and Geomembrane product lot is maintained in the electronic quality system database and the ERP software.

Quality Control Capabilities

InterWrap’s manufacturing facilities maintain a quality control system with capabilities anchored on three facets:

1. **People:** The required testing are performed by highly capable and well trained personnel. Training programs of personnel are on file for review.
2. **Equipment:** State-of-the-art equipment that is suitable for performing the required product testing. Calibration and maintenance records are on file for review.

QUALITY CONTROL

3. **Methods:** Industry standard test methods are employed to monitor the product quality.

Sampling and Inspection Plans

InterWrap has instituted a product inspection system that is guided by industry standards and by customer requirements.

A Geomembrane lot must meet both the sampling and inspection requirements to qualify for shipment. Finished Geomembrane Sampling and Testing Specifications define the minimum sampling and testing protocol for all Geomembrane products. A selection of roll samples from each manufacturing lot is retained should future testing be required. These samples have the same label information as the Geomembrane rolls. The storage method prevents the deterioration of the samples.

Inspection Records

InterWrap maintains a quality system database to collect, store and analyze the inspection data. All the inspection data are available to different work groups within the organization.

InterWrap can provide signed mill certificates for each Geomembrane lot or roll produced. The mill certificate provides the actual results for the specified quality attributes and validates that each product meets the Geomembrane roll specifications as published on the InterWrap website or as submitted by the InterWrap authorised personal to the respective customer for the respective product.

Verification and Approval.

The InterWrap quality system requires that the test results have to be reviewed and signed off or Acknowledged by approving authorities prior to shipment for their correctness within specification. This prevents the shipping of Geomembrane rolls that do not meet the product specifications.

The Quality system database indicates the status of a Geomembrane roll. The database is integrated with the shipping process through existing process controls.

When necessary, an independent verification is carried out by an external laboratory. The selection of a third-party laboratory is done in concurrence with the customer requirements.

Finished Product Packaging and Labelling


The packaging and labelling specifications are communicated to the production group through the job order # system.

The Geomembranes rolls are weather resistant and do not require further packaging. The minimum packaging and labelling requirements are indicated in the Finished Geomembrane Packaging and Labelling Specifications.

Records Control and Documentation

The documentation required to effectively implement the quality system are electronically controlled and maintained. The majority of the quality and manufacturing records are maintained electronically in soft files and hard files as well. A back-up and redundancy protocol is in place to ensure that electronic records are available and protected.

The quality system defines the accountability, method and retention period for all paper-based quality and manufacturing records.



FEATURES & BENEFITS

- SurFlex™ surface technology provides superior welding characteristics & industry leading resistance to stress cracking
- Unequaled mechanical strength, tear and puncture resistance due to our proprietary layered construction
- Low unit weight and superior seaming allows for construction of large prefabricated panels
- Environmentally responsible recovery and recycling program
- Puncture, abrasion and chemical resistant construction with a high strength HDPE woven core that provides superior dimensional stability
- Outstanding UV, ozone & oxidation resistance
- Non-toxic, no PVC or other hazardous materials used in construction of fabric
- Low water vapor permeance

Be water smart



The smart choice for water retention, containment, pond and canal lining applications.

RhinoMat is a reinforced polyethylene geomembrane that offers exceptional hydrostatic resistance for buried and unburied containment applications. For applications where liquid containment is critical, RhinoMat's durable and lightweight construction, combined with our Surflex™ technology for superior welding characteristics, will give you maximum performance in all climates and environmental conditions.

Designed for easy installation and long life, RhinoMat is an extremely durable and light weight fabric that is the ideal containment solution for applications such as:

- Irrigation and canal liners
- Golf course and decorative pond liners
- Soil remediation pads
- Daily and interim landfill covers
- Shale oil and gas development, e.g., drill pads and various liquid containment
- Oil and gas production, e.g., various secondary containment applications
- Floating covers
- Water reservoirs and ponds
- Paved and unpaved roadways
- Subgrade protection
- Temporary erosion control
- Barriers, blankets, and curtains
- Rain sheets for Ore in Mining applications
- Raincoats for heap leach pad covers
- Underslab vapor retarders



Certified to
NSF/ANSI 61

Safe for potable drinking water

**Geosynthetic
Accreditation Institute**

GAI - LAP Approved Laboratory





RhinoSkin® 30SG

RhinoSkin 30SG incorporates a high density polyethylene scrim coated two sides with a uniquely engineered low density black polyethylene blend. This design provides a full 30 mil protection plus a patented slip-resistant surface treatment "Sure-Grip™" that requires no special edge-stripping or other pre-conditioning to seam. The patented slip resistant granular surface seams flawlessly with industry standard seaming tools and provides superior walkability in wet or oily conditions.

RhinoSkin® 30SG is a high strength product specifically engineered for use as heavy-duty liners and covers for various applications including:

- Irrigation and canal liners
- Moisture barriers and covers for athletic fields
- Golf course and decorative pond liners
- Soil remediation pads
- Interim and final landfill and Mine Reclamation cover systems
- Shale oil and gas development, e.g., drill pads and various liquid containment
- Oil and gas production, e.g., various secondary containment applications
- Floating covers
- Temporary Landfill Caps
- Water reservoirs and ponds
- Paved and unpaved roadways
- Subgrade protection
- Temporary erosion control
- Barriers, blankets, and curtains
- Rain sheets for Ore in Mining applications
- Underslab vapor retarders



PATENTED
SURE-GRIP™
SURFACE TREATMENT

RhinoSkin 30SG

FEATURES & BENEFITS

- No edge-stripping required, faster seaming
- Offers true 30 mil membrane barrier
- Patented Sure-Grip™ granular surface provides superior walkability in wet or oily conditions
- Environmentally responsible recovery and recycling program
- Puncture, abrasion and chemical resistant construction with a high strength HDPE woven core that provides superior dimensional stability
- Outstanding UV, ozone & oxidation resistance
- Low water vapor permeance

RhinoSkin 12, 16, 20, 24 & 30

FEATURES & BENEFITS

- SurFlex™ surface technology provides superior welding characteristics & industry leading resistance to stress cracking
- Unequaled mechanical strength, tear and puncture resistance due to our proprietary layered construction
- Low unit weight and superior seaming allows for construction of large prefabricated panels
- Environmentally responsible recovery and recycling program
- Puncture, abrasion and chemical resistant construction with a high strength HDPE woven core that provides superior dimensional stability
- Outstanding UV, ozone & oxidation resistance
- Non-toxic, no PVC or other hazardous materials used in construction of fabric
- Low water vapor permeance



12, 16, 20, 24 & 30

RhinoSkin is InterWrap's durable line of industrial fabrics, designed for maximum strength and performance. RhinoSkin is quickly becoming the popular choice for use in high strength durability applications such as:

- Temporary irrigation liners
- Sub base liner for aggregate canals
- Daily and temporary landfill covers
- Moisture barriers and covers for athletic fields
- Soil remediation pads
- Interim and final landfill and Mine Reclamation cover systems
- Shale oil and gas development, e.g., drill pads and various liquid containment
- Water reservoirs and ponds
- Paved and unpaved roadways
- Subgrade protection
- Temporary erosion control
- Barriers, blankets, and curtains
- Underslab vapor retarders
- Field covers
- Agricultural covers
- Transportation covers




FRACKING CONTAINMENT SOLUTIONS

All of InterWrap's RPE products are designed to hold water, however, the best solution for in ground water and liquid storage is RhinoMat 500 or for longer life ponds RM 750. These two products offer the superior reliability and longevity of HDPE, the flexibility and ease of handling of PVC, and better puncture resistance than LLDPE. RhinoMat liners are lighter and can be fabricated into larger panels than PVC, LLDPE or HDPE products.

InterWrap's Reinforced Polyethylene (RPE) products are designed specifically with the energy markets of North America in mind. The primary objective has been to maximize quality and reliability while still keeping a focus on cost and value. RhinoSkin and RhinoMat products have been engineered for industry leading strength and reliability to meet the demands of the drilling fields of North America. These products incorporate ease of installation combined with capability to withstand the hottest temperatures of the Eagle Ford or the cold polar vortex in the Bakken basin. Ease of handling and use is paramount to getting jobs done on time and under budget.

RhinoSkin is a secondary containment for use as a pad liner with options to add a specially formulated "Safe-T-Grip" slip resistant walking surface. RhinoSkin is one of the strongest and most durable products available with greater puncture and tear strength than more expensive substitute products. Dollar for dollar, RhinoSkin offers the best value available on containment protection.

RhinoMat series liners are engineered with heavy duty containment in mind. RhinoMat is suitable for the most sensitive locations near precious land and water supplies to the most demanding strength requirements of above ground storage tanks. Its linear low-density polyethylene (LLDPE) film laminate structure combined with a HDPE reinforced core meets these challenges. With RhinoMat products you are insured of no pin-holing leaks, or memory creases from transportation or installation. They offer extremely high puncture and Mullen burst ratings similar to much thicker High-Density Polyethylene (HDPE) products. RhinoMat also features long term UV life expectancy for up to 20-year exposure for applications that need to hold containment of liquids and solids. RhinoMat 750 is known industry wide as the replacement for costly 30 to 40 mil LLDPE or reinforced LLDPE series liners. In fact, in comparison RhinoMat offers strong seams and higher puncture resistance than



many of products. RhinoMat can be used to build step panel liners for above ground storage tanks up to 250ft in diameter with up to 16ft high walls. Installer testimonials also claim product ease of handling and welding account for up to 20% savings in cutting and install labor. One of RhinoMat 750 primary uses is for the capping coal ash containments. The main reason for this is that RhinoMat is 25% lighter than PVC and can be fabricated into 30% larger panels reducing field seams by 60%. RhinoMat also offers far more resistant to tear propagation and has superior puncture strength. Its ability to stretch and conform to irregular surfaces also makes it an ideal product for use with Coal Ash with its inherent requirement to settle over time. RhinoMat 750 can also be third party leak detected for quality control of the site. For the energy market this means it can withstand the weight and size of cuttings pits and large multi acre ponds used in containing fresh water.

- A** RhinoMat 750 is a 30 mil RPE liner which offers superior cold weather install performance compared to competitors 30 or 40 mil LLDPE products. Furthermore, RM 750 also offers the strongest puncture resistance on the market. Rest assured that RM750 will hold water, save install time and costs, and on average will offer a 30-40% cost savings compared to other current tank lining products currently deployed.
- C** RhinoSkin 30 with Safe-T-Grip® walking surface treatment is the best low cost alternative to other anti-slip pad liners on the market. Be on budget and save time by installing a premium slip resistant system.

- B** All of InterWrap's RPE products are designed to hold water, however, the best solution for in ground water and liquid storage is RhinoMat 500 or for longer life ponds RM 750. These two products offer the superior reliability and longevity of HDPE, the flexibility and ease of handling of PVC, and better puncture resistance than LLDPE. RhinoMat liners are lighter and can be fabricated into larger panels than PVC, LLDPE or HDPE products.
- D** InterWrap's RhinoMat 500 is specifically engineered to withstand chemical elements and field abuse.

Installation guideline for factory fabricated panels out of RhinoSkin and RhinoMat . This guideline is designed to provide a minimum set of standards for site installation. However, depending on the complexity and project specific requirements, a qualified design engineering firm may be required for design and installation specifications of the geomembrane. All work shall be in accordance with the project drawings, specifications and QC requirements.

These Installation instructions are based on guidelines set out by the Fabricated Geomembrane Institute.

Applications

Typical applications for factory fabricated RhinoSkin and RhinoMat geomembranes that are less than 25 mil (0.64 mm) in thickness include but are not limited to:

- Irrigation and canal liners
- Moisture barriers and covers for athletic fields
- Golf course and decorative pond liners
- Soil remediation pads
- Interim and final landfill and Mine Reclamation cover systems
- Shale oil and gas development, e.g., drill pads and various liquid containment
- Oil and gas production, e.g., various secondary containment applications
- Floating covers
- Temporary Landfill Caps
- Water reservoirs and ponds
- Paved and unpaved roadways
- Subgrade protection
- Temporary erosion control
- Barriers, blankets, and curtains
- Rain sheets for Ore in Mining applications
- Underslab vapor retarders

ASTM References

American Society for Testing and Materials (ASTM)

1. ASTM Standards D4437. "Standard Practice for Non-destructive Testing (NDT) for Determining the Integrity of Seams Used in Joining Flexible Polymeric Sheet Geomembranes". ASTM International, West Conshohocken, PA.
2. ASTM Standards D5199. "Standard Test Method for Measuring the Nominal Thickness of Geosynthetics". ASTM International, West Conshohocken, PA.
3. ASTM Standards D751. "Standard Test Methods for Coated Fabrics". ASTM International, West Conshohocken, PA.
4. ASTM Standards D1777. "Standard Test Method for Thickness of Textile Materials". ASTM International, West Conshohocken, PA.
5. ASTM Standards D5641. "Standard Practice for Geomembrane Seam Evaluation by Vacuum Chamber". ASTM International, West Conshohocken, PA

Submittals

Documents to be included in a submittal to the owner/engineer:

1. Example material warranty and Geomembrane installation warranty.
2. Sample of Geomembrane(s) to be installed including the technical data of the product.
3. Reports of the results of examinations and testing shall be prepared and submitted to the Owner's Representative.
4. Shop drawings/panel layout for Geomembranes with panel numbers, field seam locations, corresponding to shipping labels.
5. Submit resumes or qualifications of the installation supervisor and certified welding technicians. It is recommended that the welding technicians hold an International
6. Association of Geosynthetic Installers (IAGI) Certified Welding Technician (CWT) certification.
7. Documentation to be submitted by the Fabricator varies depending on the Owner's requirements. These may include copy of tested seams, certifications, or any other document related to the quality of the Geomembranes and their installation.
8. Fabricator and Installer QC Manuals.

InterWrap Qualifications

InterWrap has been producing these products for over 30 years. RhinoSkin and RhinoMat have been in production for the last 10 years and meet the minimum requirements set by FGI of at least five years of continuous experience in the manufacture of the geomembrane and the minimum of 2,000,000 m² (21,527,820 ft²) of the specified geomembrane or similar product during the last 5 years.

Fabricators Qualifications

The fabricator of the geomembrane shall have fabricated a minimum of 250,000 m²/year (2,691,000 ft²/year) of the specified type or similar geomembranes.

Installer's Qualifications

The Geomembrane Installer shall be the Fabricator, approved Fabricator's Installer, or an installer/contractor approved by the Owner's Representative. The installer shall have a minimum experience level of 50,000 m² (538,200 ft²) using the specified geomembrane. It is the responsibility of any of the aforementioned parties to select a Geomembrane Installer with the appropriate degree of experience, personnel, and equipment to accomplish the required quality standards.

Geomembrane Arrival at Project Site

Unloading

Inspect fabricated geomembrane panels prior to unloading from vehicle at project site (e.g. type of material, conditions, etc.). Make any claims for damage with the carrier prior to unloading or shortly after geomembrane unloading. Materials delivered to site should be off-loaded (using forklift or similar equipment) in a location where minimum handling steps will be required. While unloading or transferring the fabricated panels from one location to another, prevent damage to the wrapping and the fabricated panel itself. Any damage during offloading and transferring should be documented by the contractor unloading the material and the installer.

Storage

Leave the panels packaged in UV protected wrap until the day that the panels are to be installed. If extremely hot or cold temperatures are present, keep the panels inside at a moderate temperature. This reduces the force required to unfold the panels. Fabricated panels, when possible, should be stored on pallets off the ground. The storage area should be dry, level, and with a firm base to facilitate lifting; so the panels are not damaged, do not become dirty, and remain dry externally and internally.

Installation

Subgrade Preparation

A pre-installation inspection shall be requested by the geomembrane installer and ALL interested parties before moving panels from the storage location to the placement area. If the subgrade is deemed to be inappropriate for any reason, it should be remediated prior to geomembrane movement and placement. Subgrade surfaces should be free of loose rock fragments (>10 mm or 0.4 inches), sticks, sharp objects, or debris of any kind. The surface should provide a smooth, flat, firm, unyielding foundation for the geomembrane with no sudden, sharp or abrupt changes or break in grade that can tear or damage the geomembrane. No standing water, mud, vegetation, snow, frozen subgrade, or excessive moisture is allowed before geomembrane placement. All pipes, drains, fitting, etc., which are to be installed beneath the geomembrane, should be in place, backfilled, and ready to be covered with the geomembrane before panel deployment. An anchor trench in the shape of a “U” or “V” can be used as a perimeter termination point for the geomembrane. Installation of the geomembrane shall be started from the anchor trench.

Unfolding and Deploying Prefabricated Panels

The geomembrane shall be supplied as a continuous panel with factory seams in the panel to reduce the amount of field seaming and testing. Fabricated geomembrane panels are normally placed at a starting point on one corner of the area to be lined. The deployment markings on the packaging or label indicate which direction the panel will unfold. Note accordion-folded and rolled panels will unroll in only one principal direction while double accordion-folded panels may unfold in either principal direction. While unrolling and/or unfolding the geomembrane, inspect the fabricated panel for proper material type and thickness, damage, and/or defects. Repair any damage found. Provide suitable wind uplift protection with sandbags (dirt) or other ballast (such as rolls of geotextile) after the geomembrane panel is unfolded. Only material that is to be immediately welded, i.e., during that work-day, should be deployed. Once the geomembrane is properly placed, the material should be seamed as soon as practical.

Field Seaming

A large advantage of factory fabricated geomembranes is that manufactured rolls of material can be fabricated into large panels in a factory before shipment to the project site. This minimizes the amount of the field seaming and maximizes the amount of factory seaming which results in more high quality seams. In particular, the individual widths of the manufactured geomembrane rolls shall be assembled into large panels that are custom-designed for the specific project and correspond to the panel layout diagram. If factory seaming is maximized, field seaming can be reduced by 80 to 95 %. In other words, only 5 to 20% of all seams need to be made in the field depending on the unit weight of the

geomembrane material. This reduction in field seaming improves seam quality, accelerates construction, minimizes or eliminates destructive field seam tests, reduces weather exposure issues, allows modular construction, and reduces project costs.

Field Cleaning of Seams

After the panels are initially placed in the proper position, remove as many wrinkles as practical. If possible, allow the panels to “relax” by allowing the panel to warm in the sun. The edges to be seamed need to be smooth and free of wrinkles to ensure good field seams and no “fish mouths.” An overlap of 0.15m (6 inches) for thermal seaming and 100 – 150 mm (4 – 6 inches) for tape seaming must be cleaned of all dust, dirt, water, and foreign debris no more than 30 minutes prior to the seaming operation. Only clean, soft rags should be used for cleaning the areas to be seamed. The seaming operation requires a solid, dry, smooth subsurface (see section 3.01 A Subgrade Preparation). During the cleaning operation, the Geomembrane sheets will be inspected for proper type, thickness, and defective areas which must be removed and/or repaired prior to seaming.

Field Seaming

Lightweight reinforced geomembranes are mainly used as a containment barrier for water or other liquids (see Section 1.01 C above). For this reason, seaming the geomembranes is a vital factor in the installation process. For most projects, field seams should be run perpendicular to the slope. Reinforced Factory Fabricated Lightweight Geomembrane Panels can be field seamed by either of the following methods:

- Field Thermal Seaming (automated hot edge or hot air welding machine)
- Field Tape Seaming

Extrusion welding is not included in the field seaming list because it is not recommended for geomembranes less than 40 mil (1.0 mm) thick.

Field Thermal Seaming (solid wedge only)

Thermal seaming is performed with an automated hot wedge or hot air welding machine, which uses a heated element to melt the geomembranes to be welded and then presses the two melted sheets together to form a fusion bond. When performed properly, wedge welders produce high quality and consistent seams. The wedge in a hot wedge welder can be heated with hot air (hot air method), or with electric resistance heating (hot wedge method). It is common to weld fabric supported material with a hot air wedge welder. All wedge welders employ a set point controller to accurately maintain the welding temperature within the most efficient welding temperature for the material. The pressure wheels are normally adjustable to allow for good material bonding after heating. The single (or solid) wedge arrangement produces a fully bonded weld not less than 25 mm (1 inch) in width. Seaming with a wedge welder is to be undertaken only by persons that have been trained and qualified in the use of the equipment (see section 2.01 B above). Repairs, maintenance, adjustments, and modifications are to be performed only by trained personnel. Temperature controllers on the thermal welding device should be set according to type of geomembrane, thickness, ambient temperature, type of heating (air v. wedge), rate of

seaming, and location of thermocouple within the device. It is necessary for the operator to keep constant visual contact with the temperature controls, as well as the completed seam exiting the welder to ensure adequate welding is occurring. It is not recommended to adjust welding parameters without the approval of a trial seam (See section 3.01.D.1 below).

Pre-heating of the geomembrane in the seaming area is optional. The amount or type of preheating and its timing preceding the actual seaming is at the option of the installer. Properly functioning portable electric generators must be available within close proximity of the seaming region and with adequate extension cords to complete the entire seam. These generators should be of sufficient size or number to handle all seaming electrical requirements. The generator must have rubber tires, or be placed on a smooth plate such that it is completely stable and it does not damage the geomembrane. Fuel (gasoline or diesel) for the generator must be stored away from the geomembrane, and if accidentally spilled on the geomembrane it must be removed immediately. The areas should be inspected for damage to the geomembrane and repaired if necessary.

Field Tape Seaming

Prepared tapes include mastics, putties, asphalt, and butyl tapes can be used to seam some geomembranes. Selection of the tape depends on the material being seamed and the fluid being contained. Immediately after creating a tape seam, it should be loaded or secured to facilitate bonding. The preferred method for securing prepared tape joints is to backfill the geomembrane with a suitable soil cover so tensile stresses do not develop. The backfill creates a pressure seal between the geomembrane panels and tape which is usually effective.

An alternative method of creating strength in a tape seam is to sew the seam first and then use prepared tapes to waterproof the joint. Even with a sewn seam; the recommended practice is to backfill the geomembrane to prevent shifting of the seam and to help adhere or bond the tapes. The minimum overlap of geomembrane sheets for tape seaming shall be about 0.10 m (4 inches).

Snow accumulations must be removed prior to seaming because tapes may not adhere or stick in the presence of frost or dew. To create a tape seam, place one or two continuous lines of prepared tape between the sheet overlap. Press the sheet materials together to compress the tape using a rubber hand roller or similar tool. In areas where wrinkles cannot be removed, use tapes on all sides of the wrinkle to form a waterproof seal.

Visually inspect the completed seam to ensure intimate contact between the tapes and the upper and lower sheet surfaces. Repair discontinuities by placing a patch over the damaged area with a prepared tape seal around the perimeter. The patch must be round, oval, or contain rounded corners and extend 0.15 m (6 inches) around the defect.

Supervise the backfilling of the seam area to prevent the seam from being pulled apart. Backfill should proceed in a direction that does not tend to pull the seams apart or create a shear or tensile stress in the seam.

Field Seaming Test Requirements

Test Seams (Trial Seams)

Test seams shall be prepared and tested by the Geomembrane Installer to verify that the seaming parameters are adequate at the start of each welding session or at the beginning of each working day. Test seams also may be made whenever personnel or equipment are

changed and when climatic conditions reflect wide changes in geomembrane temperature or other conditions that could affect seam quality. A minimum of one test strip per seaming apparatus shall be conducted at the start of each welding session during a day and at least every 4 hours or 3000 lineal feet of field seam per machine, whichever is more frequent.

Test seams shall be made using "scrap" material from the same lot as the geomembrane being welded in the field because the geomembrane is pre-fabricated into panels in a factory. This requirement is necessary to ensure that the installed geomembrane panels are not damaged prior to the onset of the field welding process because no destructive seam tests shall be conducted on field welded seams to preserve integrity of the fabricated panels. The test seams shall be at least 1.8 m (6 ft) long for all types of field seams. If there is no area or equipment on site to provide for these seam requirements, seam strength can be verified for production using trial welds sent to an independent testing laboratory to verify properties. If a test seam fails, an additional test seam shall be immediately completed. If the additional test seam fails, the seaming apparatus shall be rejected and not used until the deficiencies are corrected and a successful full test seam is produced.

Each test seam shall be labeled with date, geomembrane temperature, weather conditions, number of seaming unit, panel identification, seam number or test location, technician performing the test seam, and a pass or fail description. Pre-qualification seams for tape seams shall be in accordance with ASTM D7272.

Non-Destructive Testing (NDT) of Seam Testing

All Field Seams shall be non-destructively tested by the Geomembrane Installer over the full length of the seams before the seams are covered. Each seam shall be numbered or otherwise designated. The location, date, test unit, name of the technician, name of QC person, and outcome of all NDT shall be recorded and submitted to the Owner's Representative.

Testing should be performed as the seaming progresses, not at the completion of all field seaming, unless agreed to in advance by the Owner's Representative. All defects found should be repaired, re-tested, and remarked to indicate acceptable completion of repair.

NDT shall be performed using one or more of the following methods:

Air Lance Testing (ASTM D 4437)

The Geomembrane Installer shall provide an air compressor, air hose, and air lance wand with a pressure gauge capable of measuring air flow to the tip. The testing shall be performed by experienced technicians familiar with this testing procedure.

This non-destructive test involves placing the air lance wand 6 to 12 mm (¼ to ½ inch), but not more than 50 mm (2 inches), from the edge of a completed seam and closely monitoring the backside of the sheet for any air penetration through the seam, loose edges, ripples, and/or noise. If air penetrates the seam area, the technician will either see this visibly or hear it audibly and the area shall be marked for repair.

Mechanical Point Stress or "Pick" test (ASTM D4437)

This NDT uses a dull tool (such as a blunt screwdriver) under the top edge of a field seam. With care, an installer can detect an un-bonded area, which is easier to separate than a properly bonded area. Care should be taken to not damage the already bonded areas. This method must be used with extreme care so as not to damage the parent thin gauge geomembrane and is to be used only if other NDT methods are not available.

Identification of Defects

Seams shall be inspected by the geomembrane installer and the owner's representative before, during, and after field seaming to identify all dirty and wrinkled areas and any defects.

Evaluation of Defects

- i.* Each suspect location (both in geomembrane seam and non-seam areas) shall be non-destructively tested. Each location which fails non-destructive testing shall be marked, numbered, measured, and posted on the daily installation drawings and subsequently repaired.
- ii.* Defective seams, tears or holes shall be repaired by capping or cutting out the defective seam and re-seaming. Single seams in excess of 20% of their length requiring repair should be entirely removed and re-welded.
- iii.* Each patch or capping shall extend a minimum of 150 mm (6 inches) in all directions beyond the defect.
- iv.* All repairs shall be located, measured, non-destructively tested, and recorded.

Geomembrane Penetrations

Any structure or containment area built from man-made materials (metal, concrete, etc.) shall not allow protrusions, pinch points, or movement of the supporting structure that might damage the geomembrane and adversely affect the ability of the geomembrane to perform its containment function. All pipes, drains, fitting, etc., which are to be installed beneath the geomembrane, should be in place and ready to be covered with the geomembrane before geomembrane deployment. If possible, avoid cutting the geomembrane at details by using factory fabricated pipe boots that can be seamed to panels in the field. The following directions provide additional details for handling geomembrane penetrations:

i. Pipes

Whenever possible, avoid slitting geomembrane panels for piping details until a prefabricated pipe boot is ready for immediate installation. Cuts made in the geomembrane for clearance over penetrations should always be made as small as possible to minimize patch work. Generally, it is preferred to let the geomembrane straddle a relatively small protrusion (for later detail work) provided that a rag or towel is taped over the pipe to avoid damage to the geomembrane. Factory prepared pipe boots should fit snugly but not require excessive force to pull over a pipe. If a pipe boot feels overly snug but workable, try applying either talc powder or using compressed air with a nozzle to float the boot sleeve over and along the pipe. Pipe boots should never be used if the force required to install them stresses or weakens the boot. When properly installed, the pipe boot will lay flat against grade surrounding pipe without leaving pockets that may become stressed during or after placement of backfill. Pipe boot aprons should be seamed to the parent geomembrane using one of the repair techniques described in the Seaming Section above. Proper leak proof sealing of pipe boots should be verified by non-destructive methods. The pipe boot sleeve should be attached to the pipe using butyl tape between the pipe and boot and two stainless steel band clamps. When cover materials are not used (see section 3.01.F below), splash pads or additional geomembrane layers shall be used for all inflow pipes to prevent long term wear and damage to the geomembrane caused by the direct impact of the inflow on the geomembrane panels. The pads should be welded on top of the geomembrane panels

and tested according to sections 3.01.C and D, respectively. Common splash panel sizes are 1.2 to 1.8m (4 to 6 ft) in all directions. However, larger sizes may be required depending on the amount of inflow pipes and the height to the discharge point.

ii. Concrete

Where bonding a geomembrane to concrete (or masonry) is required, the concrete surface should be smooth, clean, dry, and free of any sharp protrusions or rock in the backfill. Geomembrane to concrete seals shall be accomplished with mechanical anchors (e.g. fasteners, termination bars). An approved sealant is placed between the geomembrane and the concrete surface to ensure sealing. The geomembrane fixed to a concrete structure must be on firm soil subgrade that will not deform and stretch the geomembrane. Compacting of the soil subgrade around such structures must be performed with particular care so excessive differential movement between the concrete and soil subgrade does not occur.

iii. Drains

The geomembrane shall be mechanically fastened to the concrete structure at the location of water discharge. This detail requires the installation of a concrete base or structure at the location of the drain. Where water enters or exits the geomembrane area, e.g., ponds, reservoirs, and canals, this point must have proper geomembrane termination so as not to damage the geomembrane. The area of inflow must be anchored with a trench of a depth or attached to a structure as designed by the Project Engineer or Design Professional. The geomembrane is installed and then anchored to the concrete prior to the covering with soil.

iv. Aerators

Geomembrane design in lagoons with aerators should require ballast, e.g. precast concrete slab, on the geomembrane to prevent uplift and to provide a pad to support the aerator when the water level is lowered. Many examples exist of geomembrane damage due to an aerator settling on the geomembrane or where the geomembrane was lifted into the aerator. Other aerator damage is frequently evidenced as cuts in the geomembrane along a specific elevation on the side slope where the aerators have been pulled to shore for maintenance. Geomembrane sheets are easily damaged by the sharp edges of a 6 mm (0.25 inch) thick stainless steel plate of an aerator.

Cover Materials

When placing cover material or initially filling the containment area, it is important to ballast the geomembrane into the perimeter anchor trench before covering or filling. The anchor trench or perimeter shelf area should be the last area covered to complete the cover process. Under all operating conditions, protection of the geomembrane will be required. Care should be taken when covering the geomembrane to prevent any damage. At no time will construction equipment be allowed to operate or drive directly on the geomembranes. Any damage to the geomembrane should be repaired prior to proceeding with cover material placement. Costs associated with repairs are the general contractor's responsibility. The cover material shall be placed as soon as practical, in conjunction with or upon completion of the geomembrane installation or as the installation progresses to minimize traffic on the geomembrane and damage.

Access roads for clean soil cover should be maintained to provide 0.3 m (12 inch) minimum and for heavier equipment on haul roads a minimum of 0.45 m (18 inch) preferable between the excavation equipment and geomembrane at all times. Some geomembrane

manufacturers may require a soil or a sand cover of at least 0.45 m (18 inches), so cover soil requirements should be verified before placement with the Design Professional and geomembrane fabricator.

Heavy equipment should operate on a minimum 1 m (3-foot) thick roadway where the “haul road” is established in and out of the containment area. Cover material shall consist of 12 mm (0.5 inch) minus particles, clean rounded soils or gravels free of sharp edges, sticks, metal, rubbish, and debris or foreign materials. Site specific materials or sizes may be acceptable. It is recommended that the contractor receive prior written approval of acceptance of the cover materials from a geomembrane representative and/or Design Professional before covering the geomembrane.

Cover soils should be dumped and leveled over the geomembrane and not pushed from one end to the other to minimize rolling and wrinkling of the geomembrane beneath the soils. Cover soil should always be placed from the bottom to the top of slopes to avoid stressing the geomembrane and slope stability problems. Equipment should be turned in long sweeping turns and not spun quickly to eliminate the chance of tires digging down to the geomembrane thru the cover soil and wrinkling or stretching the geomembrane. If geomembrane damage does occur during construction, cover placement, and/or filling, **DO NOT COVER IT UP.** Advise the foreman and CQA personnel so repair can be made and documented which will make doing the repair a lot easier than after cover soil placement or filling.

Field Acceptance

The Geomembrane will be accepted by the Owner's Representative when all of the following have been completed:

1. The entire installation is finished or on agreed upon subsections of the installation are finished (3.01 A through 3.01F).
1. All Installer's QC documentation is complete and submitted to the Owner.
2. Verification of the adequacy of all field seams and repairs and associated geomembrane testing is complete.

Site Clean Up and Demobilization

On completion of installation, the geomembrane installer shall dispose of all waste and scrap material in a location provided and approved by the owner. The installer should also remove all equipment used in connection with the work herein, and shall leave the premises in a neat and acceptable manner. No scrap material shall be left on the completed surface of the geomembrane or in the anchor trenches.



INTERWRAP FAMILY OF PRODUCTS

Synthetic Roofing Underlayment

Titanium® and RhinoRoof® are leading brands of synthetic roofing underlayment for use under steep sloped roofing. Our range of roofing underlayments offer up to six months uv exposure, superior walkability, lifetime warranties, ice damming protection and much more.

Protective Packaging - Wood

Lumber wrap and custom formed covers. WeatherPro® is InterWrap's brand of protective packaging for the transport and temporary storage of; lumber, plywood, kiln-dried lumber, treated wood, re-manufactured wood, I-joists & beams, structural panels, all types of sidings and other building materials.

Protective Packaging - Metal

Superior multi-layered high strength woven core metal packaging for the protection of flat sheet and coiled metal. Our Metal wraps have been engineered to withstand demanding environment, handling, and transport applications. InterWrap's line of Duramet™ and Promet™ wrap will ensure that your high grade metal arrives at its destination looking steel mill fresh!

Custom Coating & Laminating

Whether you are a leader in the paper converting market or need an engineered coating solution, depend on InterWrap for your Custom Coating and Laminating solutions. Our state-of-the-art extrusion technology gives us the ability to coat a diverse range of paper substrates with engineered lamination constructions. This includes multi-layer solutions such as foil based, paper-backed and woven scrim reinforced products.

Visit InterWrap.com for more information on these products.





Certificate SG14/04995

The management system of

International Packaging Products Pvt. Ltd.

Survey No. 380/2, Village Dapada, Silvassa - 396230,
U. T. of D. & N.H., India

has been assessed and certified as meeting the requirements of

ISO 9001:2008

For the following activities

**Manufacture and Supply of Polyolefin, Woven, Coated
and Printed Products.**

Further clarifications regarding the scope of this certificate and the applicability of
ISO 9001:2008 requirements may be obtained by consulting the organisation

This certificate is valid from 20 October 2014 until 19 October 2017
and remains valid subject to satisfactory surveillance audits.

Re certification audit due before 19 August 2017

Issue 1. Certified since 20 October 2014

Authorised by


SGS United Kingdom Ltd Systems & Services Certification
Rossmore Business Park Ellesmere Port Cheshire CH65 3EN UK
t +44 (0)151 350-6666 f +44 (0)151 350-6600 www.sgs.com

SGS 9001-8 01 0614

Page 1 of 1



0005



This document is issued by the Company subject to its General Conditions of
Certification Services accessible at www.sgs.com/terms_and_conditions.htm.
Attention is drawn to the limitations of liability, indemnification and jurisdictional
issues established therein. The authenticity of this document may be verified at
<http://www.sgs.com/en/Our-Company/Certified-Client-Directories/Certified-Client-Directories.aspx>. Any unauthorized alteration, forgery or falsification of the
content or appearance of this document is unlawful and offenders may be
prosecuted to the fullest extent of the law.



Certificate CH13/0823

The management system of

International Packaging Products Pvt. Ltd.

Survey No. 380/2, Dapada Village, Silvassa-Khanvel Road,
Silvassa-396 230 (UT of D& NH) India.

has been assessed and certified as meeting the requirements of

ISO 14001:2004

For the following activities

**Manufacture and Supply of Polyolefin, Woven, Coated
and Printed Products**

This certificate is valid from 13 July 2013 until 12 July 2016
and remains valid subject to satisfactory surveillance audits

Recertification audit due before 30 June 2016

Issue 1. Certified since July 2013

Authorised by

SGS Société Générale de Surveillance SA Systems & Services Certification
Technoparkstrasse 1 8005 Zurich Switzerland
t +41 (0)44 445-16-80 f +41 (0)44 445-16-88 www.sgs.com

Page 1 of 1



Accreditation No. SCESm 017



This document is issued by the Company subject to its General Conditions of
Certification Services accessible at www.sgs.com/terms_and_conditions.htm.
Attention is drawn to the limitations of liability, indemnification and jurisdictional
issues established therein.



KEY CONTACTS

Sales - North America & Europe:

Clive Mills - Director
Cell: +1 262 389 0695
Email: cmills@interwrap.com

Jimmie Eloff
Cell: +1 765 414 7285
Email: jeloff@interwrap.com

Tom Liberator
Cell: +1 503 789 7178
Email: tliberator@interwrap.com

Sales - India & Asia:

Neil Mukharji
Tel: +91 22 67416620 / 60 / 00
Cell: +91 9920958886
Email: nmukharji@interwrap.com

Technical Support:

Manish Khedkar
Email: mkhedkar@interwrap.com

Head Office:

1818 - 1177 West Hastings Street
Vancouver BC, Canada V6E 2K3
Toll Free: 1-800-567-9727
Telephone: 1-778-945-2888
Fax: 1-604-696-5518
Email: info@interwrap.com