



Break free from felt!™



FEATURES & BENEFITS

- 25 x Stronger than 15 lb felt
- 6 squares more per roll compared to 15 lb felt
- 17% more coverage per lap (42" width as compared to 36" for felt)
- Ease of installation – wider, lighter, more coverage per lap
- Synthetic construction is impervious to mold
- Lays flat and does not absorb water and wrinkle
- Enhanced UV protection
- No oil leaching - no hazardous material content
- Fiber grip slip-resistant walking surface
- Advanced backside non-slip coating
- Low temperature flexibility



15 LB FELT REPLACEMENT

**AIR, WATER & VAPOR BARRIER
FOR USE UNDER ASPHALT SHINGLES ONLY**

MEETS ASTM D226 & D4869



LENGTH PER ROLL:	286' / 87 m
WIDTH PER ROLL:	42" / 1.1 m
WEIGHT PER ROLL:	23.5 lbs / 10.6 kg
ROLL SIZE:	10 sq / 93 m ²
ROLLS PER PALLET:	56
PALLET WEIGHT:	1368 lbs / 620 kg

TEST & STANDARD	RHINOROOF TYPICAL VALUE	#15 LB FELT TYPICAL VALUE
Permeability ASTM E96	.05 Perms	5 Perms
Water Transmission ASTM D4869	Pass	Pass
Tear Strength ASTM D4533	MD 26 lbs (12 kg) CD 24 lbs (11 kg)	MD 2.2 lbs (1 kg) CD 0.9 lbs (0.4 kg)
Tensile Strength ASTM D751	MD 81 lbs (37 kg) CD 70 lbs (32 kg)	MD 54 lbs (24.5 kg) CD 29 lbs (13.2 kg)
Burst Strength ASTM D751	130 psi (897 kPa)	35 psi (242 kPa)
Elongation ASTM D751	MD 20% CD 20%	MD 3% CD 4%
Weight per Square ASTM D5261	2.25 lbs (1.02 kg)	11.2 lbs (5 kg)
Nominal Thickness ASTM D1777	7 mils (0.018 mm)	21 mils (0.525 mm)
Temperature Range	-70 °F to 212 °F (-55 °C to 100 °C)	14 °F to 212 °F (-10 °C to 100 °C)

InterWrap® Roofing Products Division

Charleston, SC • Vancouver, BC • Mission, BC • Montréal, QC
 Web: www.InterWrap.com/RhinoRoof | E-mail: info@interwrap.com
 Toll Free: 1 888 713 7663 | Tel: +1 778 945 2888

This product is manufactured in accordance with national standards which allow for non-critical variances in weights and measures.
 Test data is based on average taken over several production runs and should not be considered or interpreted as minimum or maximum values. Values are typical data and not limiting specifications.
 All values ± 10 %. RR_SS_11Feb2014

