

TITANIUM[®] PSU 30

SYNTHETIC ROOFING UNDERLAYMENT

PROFESSIONAL GRADE FOR USE UNDER ALL: METAL, TILE, SLATE, SHAKE & SHINGLE ROOFING

- Watertight asphalt to asphalt lap system
- Up to 6 months UV exposure rating
- Meets and exceeds ASTM D1970
- ICC ES Approved
- Class A Fire ASTM E108
- CAN/CSA A220.1
- Meets Class 4 Hail Rating
- Florida Building Code Approved
- Texas Department of Insurance
- PSU30 is an approved Polyfoam underlayment for use with Polyset[®] foam systems
- The only modified rubberized asphalt Peel & Stick with a tough and rugged surface
- All temperature performance -40°F to 240°F
- Installation temperature 40°F and above
- Synthetic construction inert to mold growth
- Cool gray surface, doesn't expand or contract

SPECIFICATIONS

LENGTH PER ROLL:	72' / 22 m
WIDTH PER ROLL:	36" / 91.4 cm
WEIGHT PER ROLL:	48 lbs / 22 kg
NET ROLL SIZE:	2 sq / 20 m ²
ROLLS PER PALLET:	25
PALLET WEIGHT:	1300 lbs / 590 kg

TECHNICAL DATA

TEST & PROPERTIES	STANDARD	TITANIUM [®] PSU30 TYPICAL VALUE
Color		Gray
Surface		Synthetic Polymer - Patented Sure-Foot [®] slip resistant nodular
Release Liner		Silicone Treated, Crinkled Poly Split Release
Weight per square		24 lbs / (10.8 kg)
Nail Sealability	ASTM D1970	Pass
Permeability	ASTM E96	0.0336
Nominal Thickness	ASTM D5147	45 Mil (1.1 mm)
Tensile	ASTM D1970	MD 100 lbs/in/ (17.5 kN/m) CD 80 lbs/in (14 kN/m)
Thermal Stability	ASTM D1970	240° F (115° C) Pass
Low Temp Flexibility	ICC AC 48	Pass
Tear Resistance	ASTM D1970	MD 140/ CD 100 lbf (622/445 N)
Adhesion to Plywood	ASTM D903	4 lb/in (700 N/m)
Temperature Range		-40°F to 240°F (-40°C to 115°C)

Premium Self Adhered Underlayment
for Protection from Wind Driven Rain,
Water, Snow and Ice Dams



*See www.InterWrap.com/LifetimeWarranty for complete coverage and restrictions



InterWrap[®] Roofing Products Division

Charleston, SC • Vancouver, BC • Mission, BC • Montréal, QC
 Web: www.InterWrap.com/titanium | E-mail: info@interwrap.com
 Toll Free: 888 713 7663 | Tel: 778 945 2888



This product is manufactured in accordance with national standards which allow for non-critical variances in weights and measures.
 Test data is based on average taken over several production runs and should not be considered or interpreted as minimum or maximum values. Values are typical data and not limiting specifications.
 All values ± 10%. PSU30_SS_6June2014