



**U15**

# RhinoRoof®

**SYNTHETIC ROOFING UNDERLAYMENT**

*Break free from felt!*™



## FEATURES & BENEFITS

- Meets ASTM D4869 & D226 Types I & II
- Fiber grip slip-resistant walking surface
- Enhanced UV - 60 days exposure
- 25 x stronger than 15 lb felt
- 6 squares more per roll compared to 15 lb felt
- 17% more coverage per lap (42" width as compared to 36" for felt)
- Ease of installation – wider, lighter, more coverage per lap
- Synthetic construction inert to mold growth
- Lays flat and does not absorb water and wrinkle
- No oil leaching - no hazardous material content
- Class A Fire - ASTM E108 (as part of a system)
- Contributes to LEED® points
- Texas Department of Insurance
- Advanced backside non-slip coating
- Low temperature flexibility

**MEETS ASTM D4869 & D226 TYPES I & II  
FOR USE UNDER SHINGLE, METAL & SHAKE ROOFING**



LENGTH PER ROLL:	286' / 87 m
WIDTH PER ROLL:	42" / 1.1 m
WEIGHT PER ROLL:	23.5 lbs / 10.6 kg
ROLL SIZE:	10 sq / 93 m <sup>2</sup>
ROLLS PER PALLET:	56
PALLET WEIGHT:	1368 lbs / 620 kg

CAN/CSA A123.3

FBC #FL15216



### \*TEST & STANDARD

### RHINOROOF TYPICAL VALUE

### #15 LB FELT TYPICAL VALUE

Permeability ASTM E96	.05 Perms	5 Perms
Water Transmission ASTM D4869	Pass	Pass
Tear Strength ASTM D4533	MD 33 lbs (15 kg)   CD 24 lbs (11 kg)	MD 2.2 lbs (1 kg)   CD 0.9 lbs (0.4 kg)
Tensile Strength ASTM D751	MD 88 lbs (40 kg)   CD 70 lbs (32 kg)	MD 54 lbs (24.5 kg)   CD 29 lbs (13.2 kg)
Burst Strength ASTM D751	158 psi (1089 kPa)	35 psi (242 kPa)
Elongation ASTM D751	MD 20% CD 20%	MD 3% CD 4%
Weight per Square ASTM D5261	2.25 lbs ( 1.02 kg)	11.2 lbs (5 kg)
Nominal Thickness ASTM D1777	7 mils (0.18 mm)	21 mils (0.525 mm)
Service Temperature Range	-40 °F to 240 °F (-40 °C to 115 °C)	

### InterWrap® Roofing Products Division

Charleston, SC • Vancouver, BC • Mission, BC • Montréal, QC  
 Web: [www.InterWrap.com/RhinoRoof](http://www.InterWrap.com/RhinoRoof) | E-mail: [info@interwrap.com](mailto:info@interwrap.com)  
 Toll Free: 888 713 7663 | Tel: +1 778 945 2888

\*This product is manufactured in accordance with national standards which allow for non-critical variances in weights and measures.  
 Test data is based on average taken over several production runs and should not be considered or interpreted as minimum or maximum values. Values are typical data and not limiting specifications.  
 All values ± 10%. RRU15 SS 28Nov2014