



DURATHENE™

Regular Weave PE Fabric

InterWrap Inc.
32923 Mission Way
Mission, B.C. V2V 6E4
CANADA

Phone: 604-820-5400
Fax: 604-820-5420
Web: www.interwrap.com

Product Specification Sheet

IFL100200

A high strength 10 x 10 reinforcing high density polyethylene scrim coated both sides with a uniquely engineered low density polyethylene blend.

PRODUCT SPECIFICATIONS

CODE	IFL100200
NOMINAL WEAVE	10 x 10 ppi (39 x 39 tapes per 10 cm)
COATING	Two Sides LDPE @ 1.75-2.0 mil thickness, 43.75 – 50.0 g/m ²
COLOR	Black, Silver, White
WEIGHT	221 - 233 g/m ² ± 5 % (6.5 – 6.9 oz/yd ² ± 5%) finished weight
WIDTHS	Up to 144"

PRODUCT PERFORMANCE

TENSILE STRENGTH ASTM D751-95			
Machine Direction	Force	209 lbs.	95 kg
	Elongation	20 %	
Cross Direction	Force	198 lbs.	90 kg
	Elongation	20 %	
TRAPEZOIDAL TEAR STRENGTH ASTM D4533-91			
Machine Direction	Force	66 lbs.	30 kg
Cross Direction	Force	62 lbs.	28 kg
UV ACCELERATED WEATHERING ASTM G154-98			
More than 90 % Strength Retained After 2,000 hours* Exposure			
MULLEN BURST ASTM D751-95		340 psi	2345 kPa
NOMINAL THICKNESS		14 mils	0.36 mm

Note: all values are ± 10%

* QUV A-340 lamps 8hrs UV @60 °C, 4hrs Condensation @40 °C

The test data is based on an average taken over several production runs and should not be considered or interpreted as minimum or maximum values. Values are typical data and not limiting specifications.