



# DURATHENE™

## Regular Weave PE Fabric

InterWrap Inc.  
32923 Mission Way  
Mission, B.C. V2V 6E4  
CANADA

Phone: 604-820-5400  
Fax: 604-820-5420  
Web: [www.interwrap.com](http://www.interwrap.com)

## Product Specification Sheet

### IFP150200

A 10 x 5 reinforcing polypropylene scrim coated both sides with a uniquely engineered polypropylene blend.

#### PRODUCT SPECIFICATIONS

<b>CODE</b>	IFP150200
<b>NOMINAL WEAVE</b>	10 x 5 ppi (39 x 20 tapes per 10 cm)
<b>COATING</b>	Two Sides PP @ 1.0 mil thickness, 25g/m <sup>2</sup>
<b>COLOR</b>	Clear
<b>WEIGHT</b>	107 g/m <sup>2</sup> ± 5 % (2.8 oz/yd <sup>2</sup> ± 5%) finished weight
<b>WIDTHS</b>	Up to 144"

#### PRODUCT PERFORMANCE

TENSILE STRENGTH ASTM D751-95			
Machine Direction	Force	125 lbs.	57 kg
	Elongation	20 %	
Cross Direction	Force	97 lbs.	44 kg
	Elongation	20 %	
TRAPEZOIDAL TEAR STRENGTH ASTM D4533-91			
Machine Direction	Force	40 lbs.	18 kg
Cross Direction	Force	31 lbs.	14 kg
UV ACCELERATED WEATHERING ASTM G154-98			
More than 80 % Strength Retained After 2,000 hours* Exposure			
MULLEN BURST ASTM D751-95		185 psi	1276 kPa
NOMINAL THICKNESS		5.25 mils	0.13 mm

Note: all values are ± 10%

\* QUV A-340 lamps 8hrs UV @60 °C, 4hrs Condensation @40 °C

The test data is based on an average taken over several production runs and should not be considered or interpreted as minimum or maximum values. Values are typical data and not limiting specifications.