



# Promet<sup>®</sup> CLASSIC<sup>™</sup>

## IV. PRODUCT SPECIFICATION SHEET

A reinforcing high density polyethylene scrim coated both sides with a uniquely engineered low density polyethylene blend and laminated to natural kraft paper impregnated with a proprietary VCI formulation engineered to prevent the corrosion of metals.

### PRODUCT SPECIFICATIONS

<b>Nominal Weave</b>	5 x 2 ppi (20 x 10 tapes per 10 cm)
<b>Coating</b>	Two Sides @ 0.8 - 1.0 mil thickness, 20 - 25 g/m <sup>2</sup>
<b>Color</b>	Clear, Grey, White
<b>Weight</b>	140 g/m <sup>2</sup> ± 5 % (4.12 oz/yd <sup>2</sup> ± 5 %) finished weight
<b>Widths</b>	Up to 144"

### PRODUCT PERFORMANCE

#### Tensile Strength ASTM D751-95

Machine Direction	Force	106 lbs.	48 kg
	Elongation	18 %	
Cross Direction	Force	77 lbs.	35 kg
	Elongation	18 %	

#### Trapezoidal Tear Strength ASTM D4533-91

Machine Direction	Force	55 lbs.	25 kg
Cross Direction	Force	35 lbs.	16 kg

#### UV Accelerated Weathering ASTM G154-98

More than 90 % Strength Retained After 2,000 hours\* Exposure

<b>Mullen Burst ASTM D751-95</b>	130 psi	897 kPa
<b>Nominal Thickness</b>	8.0 mils	0.2 mm

Note: all values are ± 10%

\* QUV A-340 lamps 8 hrs UV @ 60°C, 4 hrs Condensation @ 40°C

The test data is based on an average taken over several production runs and should not be considered or interpreted as minimum or maximum values. Values are typical data and not limiting specification.

**Head Office**  
32923 Mission Way  
Mission  
British Columbia  
Canada V2V 6E4

**USA and Canada**  
Tel: 1 800 567 9727  
Fax: 1 604 820 5420  
Email: info@interwrap.com

**Global**  
Tel: 1 246 436 9522  
Fax: 1 246 431 9748  
Email: export@interwrap.com

[www.interwrap.com](http://www.interwrap.com)